



TECHNICAL DATA SHEET

TYROLIT DUO 30



Tyrolit Construction Products GmbH
Swarovskistrasse 33 | 6130 Schwaz | Austria
Tel: +43 5242 606-0 | E-Mail: construction@tyrolit.com

TYROLIT Duo 30: Premium concrete densifier and hardener with protection (Hybrid-Silicate)

Description

TYROLIT Duo 30 is a highly reactive hybrid-silicate with an integrated protection against stains. The product provides the highest surface hardening of all TYROLIT silicates used for final silicization of cementitious surfaces. TYROLIT Duo 30 is used most on power trowelled, as well as on grinded/polished concrete floors as a final treatment.

Properties

TYROLIT Duo 30 penetrates deep into the surface and reacts then with free lime to calcium silicate hydrate (CSH), which progressively hydrated to a glass-like crystalline structure. Improved abrasion resistance, dust-freeness, impermeable and more resistance on the surface you get after the treatment with TYROLIT Duo 30.

The hybrid-silicate improves the density and hardness of concrete. The product reduces the penetration of liquids and dirt more as with conventional densifiers. TYROLIT Duo 30 also reduces the penetration of chlorides and therefore it improves the surface to a better frost and de-icing salt resistance.

Basically, the product causes no or only slight color enhancement. The water absorption is reduced, the surface diffusion remains open.

Field of Application

TYROLIT Duo 30 is applicable to all calcareous floor coverings, such as grinded/polished and trowelled concrete floors / cementitious screeds, terrazzo tiles / terrazzo, etc. Applications are e.g. industrial floors, market halls, logistic centers, supermarkets and in private homes, indoor and outdoor use. For high-quality stain protection, we recommend our special impregnator TYROLIT Premium Sealer 400 as an additional application.

Note: The acid sensitivity of the surfaces still remains, but will be reduced a little bit.

Processing

The surface to be treated must be dry, firm, clean, absorbent and free from oil, grease and other as a release agent acting impurities. To ascertain the consumption, make a separate sample area of the same surface. Apply the product with a pump sprayer (like-wise airless) and a suitable nozzle (0,2 - 0,3 is recommended). Work hand in hand with a second person, which is using a micro-fiber mop or a soft bristle broom to spread the material to a uniform wetting. Keep the surface moist/wet (not flooded) with material for approx. 20-30 minutes. Avoid puddles during application, but keep surface saturated. Remove surplus material after approx. 30 minutes with auto scrubber machine or rub into the floor with a buffing pad. Dried up excess creates white residues, which must be removed immediately. Drying time will be around 1-2 hours. For very high absorbent floors a double treatment with TYROLIT Duo 30 is recommended. Second application must be fresh in fresh (wet in wet), as the product builds up its repellent effect very quickly.

Note: Adjacent surfaces must be protected against splashes. Remove surplus material film before drying up. Clean equipment with water.

Processing temperature

Avoid direct solar radiation during processing. The surface temperature should be between 5 ° C and 35 ° C (40 – 100 F). Floor heating maybe turn off. Avoid direct moisture until the treatment is totally dry.

Drying time

The drying time (walkable) is between 1-2 hours. According to ambient temperature and humidity, drying time can vary. For completely curing or if an additional impregnation/sealer is applied after TYROLIT Duo 30 (e.g. TYROLIT Premium Sealer 400) the waiting time is approx. 12 – 24 hours.

Productiveness

Depending on the absorption following values are to be assumed. A second application halved the coverage. Reference value:

Grinded/polished surface (application at grit 100 or 200: approx. 7 - 15 m² / liter; power trowelled or even higher polished surfaces: approx. 15 - 25 m² / liter

Storage

Protect from frost. Shelf-life in cool, dry and closed container is about 12 months. Opened cans should be worked up as soon as possible.

Environmental Protection

Not empty into drains. WGK 1 (low water endangering). Waste codes/waste designations according to EWC/AVV. 06 02 05* other bases: *Evidence for disposal must be provided. Dispose of waste according to applicable legislation. Completely emptied packages can be recycled.

Security

TYROLIT Duo 30 is harmless to health after drying up. A good ventilation should be provided during and after the processing. Observance of special security measures if the product will be use in a spraying application. Safety data sheet available for professional user on request.

Ingredients: lithium hydroxide, potassium methylsilanetriolate, silicic acid, potassium salt

Labelling according to Regulation (EC) No. 1272/2008 [CLP]. Causes skin irritation. Causes serious eye damage. Do not breathe dust/fume/gas/mist/vapors/spray. Wash with water thoroughly after handling. Wear protective gloves/protective clothing/eye protection/face protection. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If skin irritation occurs: Get medical advice/attention. Take off contaminated clothing and wash it before reuse.

Identification marking for transportation:

PU	PU-marking	Transport documents
a	not applicable no dangerous goods	not applicable no dangerous goods

Packaging Unit (PU)

- a) 20 liter PE canister
- b) 200 liter barrel (on request)
- c) 1.000 liter container (IBC) (on request)

This information should only be a non-binding advice. The use of the products is based on local circumstances and on the surface itself. If there is no experience, and in cases of doubt, we recommend to try the product on an inconspicuous spot.